

Ref: PetEx.Spec.015

BITUMEN VG 30 SPECIFICATIONS

Sr.No.	Parameters	Test Method	Standard Specification	Observations / Reported Value
1.	Penetration at 25°C, 0.1 mm, 100g, 5sec,	IS 1203	Min 45	48
2.	Absolute Viscosity @60°C, Poise	IS 1206 (part 2)	2400 - 3600	2800
3.	Kinematic Viscosity @135°C, cSt, min	IS 1206 (part 3)	350	385
4.	Flash Point (Cleveland Open Cup) Type, °C, min	IS 1209	220	320
5.	Solubility in Trichloroethylene, % min	IS 1216	99	99.7
6.	Softening Point (R&B), °C, min	IS 1205	47	49
7.	Viscosity Ratio @60°C, max	IS 1206 (part 2)	4	1.19
8.	Ductility @25°C, cm, min	IS 1208	40	94

1. To buy the product in PetEx, following conditions need to be fulfilled:

- a. The Purchaser should be a member of PetEx.
- b. The Member should pay EMD (Margin money) of the price of product, as stated in the contract.
- c. The Member should have valid GST Registration
- d. The buyer should have all other valid license for his factory / storage premises.
- e. The Product with this specification is offered for sale.

2. For any clarification on membership, product and procedure, you may call to Mr. Nilesh – M : 9920494214 or logon to www.petexindia.com.